

## **PBA74 BEIGE**



## **General Description**

Beige medical grade polyurethane/urethane blend,breathable embossed film

Property	Typical Value
Thickness (micron)	152
Film weight (g/m²)	74
MVTR. upright (g/m² per 24 shrs @ 37°C/98.6°F)	1600
Tensile strength MD (gf/cm)	1000
Tensile strength TD (gf/cm)	500
Nominal length at max width (lm)	1500
Maximum width (mm)	1220
Minimum width (mm)	250
Carrier	Net interleave only
Liner	N/A
Adhesive	N/A
Elongation at break, MD (%)	240
Elongation at break, TD (%)	300

info@delstarmedical.com delstarmedical.com DELMD\_TDS\_V01\_20240319 Copyright ®Mativ Holdings, Inc. (2024). All Rights Reserved. Delstar™ is trademarks of Mativ Holdings, Inc. ("Mativ") or an affiliated company of Mativ.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

